

**AMENDMENTS TO THE SPECIFICATION:**

**Please replace Table 3, page 63 of the specification with the following re-written Table**

**3.**

**Table 3**

C. Ex No.	Graft Copolymer							Property of Molded Product		
	Graft Copolymer (A)		Graft Copolymer (B)		Mixing Method	Graft Copolymer (A)/Graft Copolymer (B) (Weight ratio)	Feature	Plane Impact Strength (*)	Izod Strength	
	Content of Rubbery Copolymer (a') (wt.%)	Mean Particle Size (μm)	Content of Rubbery Copolymer (a') (wt.%)	Mean Particle Size (μm)					23°C (kJ/m <sup>2</sup> )	0°C (kJ/m <sup>2</sup> )
6	70	0.27	70	0.08	Po. Mix.	30/70	(a)	5%	11	6.9
7	70	<del>0.27</del> 0.26	70	<del>0.08</del> 0.07	La. Mix.	30/70	(b)	0%	8.4	6.7
8	70	0.27	70	0.08	Po. Mix.	70/30	-	35%	50	10.5
9	70	0.27	-	-	-	100/0	-	15%	55	9.5
10	-	-	70	0.08	-	0/100	-	80%	20	8.1
11	70	<del>0.22</del> 0.24	-	-	-	0/100	(c)	30%	50	10.1
12	30	<del>0.27</del> 0.25	30	<del>0.08</del> 0.10	La. Mix.	30/70	-	25%	30	7.6